

Applicant: JUHUA SHOES CO.,LTD.
XIBIAN INDUSTRIAL DISTRICT,
CHENDAI TOWN,JINJIANG CITY,
FUJIAN,CHINA
Attn: LILY

Date: Jul 12, 2021

Sample Description:

Three (3) pairs of submitted samples said to be Men's Cemented lace up low cut safety shoes in Black.

Standard : ASTM F2913-19
Size : US 9
Buyer's Name : --
Ref. No : 200134/200134W
Brand : --
Manufacturer : --
Colour : --
Vendor : --
Supplier : --
P.O. No. : --
Ref. : --
Country Of Origin : --
Goods Exported To : U.S.A.
Date Received/Date Test Started: Jul. 05, 2021
Date Final Information Confirmed: --

Conclusion:

<u>Test Item</u>	<u>Result</u>
Slip Resistance	Pass

Should you have any query on this report, you may contact at gzfootwear@intertek.com

Authorized By:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch



Guiliang Dong
Senior Lab Manager



/nicoleho



Slip Resistance (ASTM F2913-19, Olean Quarry Tile Surface, Vertical Force: 500 N, 22 °C, 50% R.H)

	<u>Left(Dry Then Wet)</u>	<u>Right(Wet Then Dry)</u>	<u>Skecher USA Requirement</u>
Forepart Dry	0.89	0.88	Min. 0.60
Forepart Wet	0.72	0.71	Min. 0.50
Heelpart Dry	0.89	0.88	Min. 0.60
Heelpart Wet	0.74	0.74	Min. 0.50
		Left	
Forepart Wet Oily (#1)		0.40	Min. 0.40
Heelpart Wet Oily (#1)		0.40	Min. 0.40

Remark: #1= 25 ml Of Distilled Water With 2 Drops (0.05 g) Of Vegetable Oil

Note:

It Must Be Noted That The Slip Resistance Test Carried Out In This Report Denotes An Indication Of Slip Of This Particular Footwear/Component On The Surface Mentioned In The Test Item. It Is Important To Note That Footwear Is Subject To Many Different Conditions Encountered In Everyday Use And That It Is Impossible To Make Footwear Resistant To Slip In All Conditions. Nevertheless, It Is Generally Accepted That Problems Are Minimized If The Guideline Coefficients Of Friction Are Achieved.





End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

